

LISTING OF THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) An electrode-built-in susceptor comprising:
a susceptor base member which is made of an ~~aluminium~~ aluminum-nitride-group-sintered-member on one ~~of which~~ surface of which a plate sample is mounted;
an inner electrode which is built in the susceptor base member; and
a power supplying terminal which is disposed in the susceptor base member so as to be attached to the inner electrode, wherein
the power supplying terminal is made of a conductive ~~aluminium~~ aluminum-nitride-tantalum-nitride-composite-sintered-member containing 50 to 98 weight percent of tantalum-nitride.
2. (Currently Amended) An electrode-built-in susceptor according to Claim 1 wherein the susceptor base member is formed by a mounting plate which is made of an ~~aluminium~~ aluminum-nitride-group-sintered-member on one of which main surface a plate sample is mounted and a supporting plate which is made of an ~~aluminium~~ aluminum-nitride-group-sintered-member which is attached to the mounting plate unitarily.
3. (Currently Amended) An electrode-built-in susceptor according to Claim 1 wherein the inner electrode is made of a conductive ~~aluminium~~ aluminum-nitride-tantalum-nitride-composite-sintered-member containing 50 to 98 weight percent of tantalum nitride or a conductive ~~aluminium~~ aluminum-nitride-tungsten-composite-sintered-member containing 58 to 80 weight percent of tungsten.

Claims 4 and 5 (Canceled)

6. (Currently Amended) ~~Method~~ A method for manufacturing an electrode-built-in susceptor comprising ~~the steps of~~:
making a mounting plate for mounting a plate sample thereon and a supporting plate for supporting ~~[[a]]~~ the mounting plate by an ~~aluminium~~ aluminum-nitride-group-sintered-member;
forming a through hole on the supporting plate;

inserting a power supplying terminal which is made of a conductive ~~aluminium~~
aluminum-nitride-tantalum-nitride-composite-sintered-member containing 50 to 98 weight
percent of tantalum nitride in the through hole so as to fix the power supplying terminal
therethrough;

applying a member which contains a conductive powder on a main surface of the
supporting plate such that the conductive powder contacts the power supplying terminal;

attaching the mounting plate to the supporting plate via the member which contains the
conductive powder; and

heating the mounting plate and the supporting plate under a compressed-atmosphere
condition so as to form an inner electrode between the supporting plate and the mounting plate
unitarily.

7. (Currently Amended) ~~Method~~ A method for manufacturing an electrode-built-in
susceptor comprising ~~the steps of~~:

making a green body for a mounting plate for mounting a plate sample thereon and a
green body for supporting the mounting plate by a slurry which contains an ~~aluminium~~
aluminum-nitride-group-powder;

forming a through hole on the green body for the supporting plate;

sintering the green body;

filling an ~~aluminium~~ aluminum-nitride-tantalum-nitride-composite-sintered-member
containing 50 to 98 weight percent of tantalum nitride as a power supplying terminal in the
through hole;

applying a member which contains a conductive powder on a main surface of the green
body for the supporting plate such that the conductive powder contacts the ~~aluminium~~
aluminum-nitride-tantalum-nitride-composite-sintered-member;

attaching the green body for the mounting plate to the green body for the supporting plate
via the member which contains the conductive powder; and

heating the green body for the mounting plate and the green body for the supporting plate
under a compressed-atmosphere condition so as to form an inner electrode between the
supporting plate and the mounting plate which are made of an ~~aluminium~~ aluminum-nitride-
group-sintered-member unitarily, said inner electrode being an ~~aluminium~~ aluminum-nitride-
tantalum-nitride-composite-sintered-member.